

09/744684

525 Rec'd PCT/PTO 29 JAN 2001

LAW OFFICES
SUGHRUE, MION, ZINN, MACPEAK & SEAS, PLLC

2100 PENNSYLVANIA AVENUE, N.W.

WASHINGTON, DC 20037-3213

TELEPHONE (202) 293-7060

FACSIMILE (202) 293-7860

www.sughrue.com

January 29, 2001

BOX PCTAssistant Commissioner for Patents
Washington, D.C. 20231PCT/JP99/04028
-filed July 27, 1999

Re: Application of Eiichi KITAZONO, Hiroyoshi MINEMATSU, Takeyuki KAWAGUCHI and Takanori MIYOSHI
ADHESIVE AGENT COMPOSITION, AND PERMEABLE ADHESIVE TAPE,
ADHESIVE DRUG COMPOSITION AND ADHESIVE TAPE PREPARATION
CONTAINING THE ADHESIVE AGENT COMPOSITION
Our Ref: Q62906

Dear Sir:

The following documents and fees are submitted herewith in connection with the above application for the purpose of entering the National stage under 35 U.S.C. § 371 and in accordance with Chapter II of the Patent Cooperation Treaty:

- ☒ an executed Declaration and Power of Attorney.
- ☒ an English translation of the International Application.
- ☒ International Preliminary Examination Report.
- ☒ an English translation of Article 34 amendments (annexes to the IPER).
- ☒ an executed Assignment and PTO 1595 form.
- ☒ International Search Report, PTO Form 1449 listing the ISR references, and a complete copy of each reference.

It is assumed that copies of the International Application, the International Search Report, the International Preliminary Examination Report, and any Articles 19 and 34 amendments as required by § 371(c) will be supplied directly by the International Bureau, but if further copies are needed, the undersigned can easily provide them upon request.

The Government filing fee is calculated as follows:

Total claims	51	-	20	=	31	x	\$18.00	=	\$558.00
Independent claims	1	-	3	=		x	\$80.00	=	\$80.00
Base Fee									\$860.00
Multiple Dependent Claim Fee									\$270.00

TOTAL FILING FEE

\$1688.00

Recordation of Assignment

\$40.00

TOTAL FEE

\$1728.00

Checks for the statutory filing fee of \$1688.00 and Assignment recordation fee of \$40.00 are attached. You are also directed and authorized to charge or credit any difference or overpayment to Deposit Account No. 19-4880. The Commissioner is hereby authorized to charge any fees under 37 C.F.R. §§ 1.16, 1.17 and 1.492 which may be required during the entire pendency of the application to Deposit Account No. 19-4880. A duplicate copy of this transmittal letter is attached.

Priority is claimed from July 29, 1998 and October 14, 1998 based on JP Application Nos. 10-214058 and 10-291971, respectively.

Respectfully submitted,

Waddell A. Biggart / *Bruce E. Kram*
Waddell A. Biggart
Registration No. 24,861

WAB/plr

DESCRIPTION

ADHESIVE AGENT COMPOSITION, AND PERMEABLE ADHESIVE TAPE,
ADHESIVE DRUG COMPOSITION AND ADHESIVE TAPE PREPARATION
5 CONTAINING THE ADHESIVE AGENT COMPOSITION

Technical Field

The present invention relates to an adhesive agent
composition and a permeable adhesive tape containing the
10 adhesive agent composition, an adhesive drug composition
containing the adhesive agent composition, and an
adhesive tape preparation containing the adhesive drug
composition.

The present invention relates in more detail to an
15 adhesive agent composition having good adhesion to the
human skin and high permeability, a permeable adhesive
tape having an adhesive layer that contains the adhesive
agent composition, showing firm adhesion to the skin and
excellent in permeability, an adhesive drug composition
20 containing the adhesive agent composition, and an
adhesive tape preparation having an adhesive drug layer
that contains the adhesive drug composition, showing firm
adhesion to the skin and excellent in permeability.

25 Background Art

The following materials have been actively
developed: an adhesive agent composition and adhesive
drug composition having good adhesion to the human skin
and suitable permeability; a permeable adhesive tape
30 having an adhesive layer that contains the adhesive agent
composition; and an adhesive tape preparation having an
adhesive drug layer that contains a drug, particularly a
drug to be administered into a living body through the
skin. Rubber-based, silicone-based, acrylic-based, vinyl
35 acetate-based, vinyl ether-based and the like material-
based adhesive agents have been used as the adhesive
agents for the adhesive agent compositions and the

adhesive drug compositions for the tape preparations. Of these adhesive agents, acrylic adhesive agents that show less stimulation of the skin and that are less costly are preferably used. Moreover, in order to increase the transfer to the skin of the drug in an adhesive tape preparation containing a cutaneous absorption drug, the tape preparation must be surely affixed to the skin surface. However, for an adhesive tape preparation having excessively firm adhesion strength, the corneum is sometimes peeled off to give strong stimulation of the skin when the tape preparation is peeled off the skin. In order to solve the problem, in the development of an acrylic adhesive tape preparation, the skin touch of the tape preparation should be made soft when it is allowed to adhere to the skin; moreover, in order to increase the cutaneous absorption of a drug, the adhesive agent is allowed to contain a large amount of the liquid component. For example, substances such as sorbitan esters, aliphatic esters and polyhydric alcohols are known to have the effect of promoting cutaneous absorption of drugs, and adhesive tape preparations in which the acrylic adhesive agents are allowed to contain such cutaneous absorption promoters of drugs as the above sorbitan esters have been disclosed (Japanese Unexamined Patent Publication (Kokai) Nos. 1-233212, 1-233213, 2-196714 and 2-233617). However, as a result of allowing the adhesive agent to contain such a known cutaneous absorption promoter of a drug, there arise problems as explained below. The cohesive force of the adhesive agent is lowered, and part of the adhesive layer remains, that is, retention of the adhesive layer takes place when the tape preparation is affixed to the skin and peeled off; moreover, the liquid component containing the above cutaneous absorption promoter of a drug oozes out of the adhesive layer.

Various investigations on the methods of improving the cohesive force of the acrylic adhesive agents have

been carried out. One of the known methods is to subject the adhesive layer to a physical procedure such as irradiation with ultraviolet rays, an electron beam, radioactive rays or the like. These procedures such as
5 irradiation of ultraviolet rays sometimes cause decomposition of the drug; therefore, they are not preferable ones for the adhesive agents for medical treatment.

There are other chemical procedures for improving
10 the cohesive force of the acrylic adhesive agents. Japanese Unexamined Patent Publication (Kokai) No. 3-220120 discloses, as one of the procedures, a method of cross-linking a metal alcoholate, a metal chelate compound and/or isocyanate, etc. with a carboxyl group in
15 an acrylic adhesive polymer. In addition to these procedures, it is known that substances such as metal salts, organic peroxides, polyurethanes and/or multifunctional compounds can be used to improve the cohesive force of the acrylic adhesive agents. However,
20 when substances such as metal alcoholates, metal chelate compounds, isocyanates, polyurethanes and/or multifunctional compounds are used in combination with a drug having a functional group, there arise the problems that the substances and the drug mutually act to lower
25 the cutaneous absorption of the drug, and that the adhesive agent does not show the effect of improving the cohesive force.

Furthermore, the adhesive tape preparation used for the cutaneous absorption of a drug is very excellent in
30 administering a drug that requires continuous administration over a long period of time, an antiphlogistic antalgic that causes gastroenteropathy in oral administration, and a drug that is substantially decomposed at the initial pass in the liver. However,
35 when the adhesive tape preparation is continuously affixed to the skin of a patient over a long period of time, there arises the problem that poisoning and

itchiness of the skin appear.

5 In order to improve the prevention of poisoning the
skin, it has heretofore been attempted to make the
contents of the remaining monomers and remaining solvent
as small as possible. It is fundamentally desirable to
increase the permeability (dissipation of moisture) of
the affixed agent and suppress the humidity (poor
dissipation of moisture) of the skin in the affixed
portion. However, when the sealing degree of the affixed
10 agent is decreased by increasing the permeability, the
cutaneous absorption amount of the drug is extremely
decreased to create the inconvenience that achieving the
initial object of the tape preparation becomes
unsatisfactory. In order to keep the cutaneous
15 absorption amount of the drug at a desired value, such a
substrate having substantially no permeability or low
permeability as a PET film is used in combination with a
permeable adhesive layer when a nonpermeable adhesive
agent is used or such an adhesive agent having
20 permeability as an acrylic adhesive agent is used.

A so-called poultice has been known as an adhesive
tape preparation causing relatively less poisoning of the
skin. The poultice comprises a permeable water-
containing gel adhesive layer that contains a polyacrylic
25 acid salt or polyvinyl alcohol and a substrate showing
good air permeability and stretchability such as an
unwoven fabric with the adhesive layer formed on the
fabric. A poultice containing, in the water-containing
gel adhesive agent layer, indomethacin or ketoprofen as a
30 medicinally effective component has been widely used as
an antiphlogistic antalgic poultice in recent years.
However, since the poultice shows weak adhesion to the
skin, it has the following disadvantages: an auxiliary
means is necessary for continuously affixing the
35 poultice; and the gel becomes sticky when the ambient
temperature rises. Therefore, an antiphlogistic antalgic
tape agent has been proposed (specifications in WO

93/04677 and WO 96/08245) and practically used in place of the antiphlogistic antalgic poultice.

5 A rubber-based adhesive agent having a high cohesive force and high adhesion is used for the adhesive layer of such a tape preparation, and a fabric (preferably a knitted fabric) having a high stretchability is used as the substrate. As a result, the tape preparation alone can be affixed to a flexible portion such as the cubitus of a patient, and the affixed state can be maintained.

10 However, the rubber-based adhesive agent substantially has no permeability. Therefore, the cutaneous absorption of a drug of the tape preparation is improved at the cost of the permeability. Moreover, in general, a relatively low molecular weight chemical
15 substance such as a tackifier must be added to the rubber-based adhesive agent. Such an additive is considered to be a main cause of poisoning of the skin.

Such adhesive agents having a strong cohesive force and sufficient adhesion to the skin as a silicone-based,
20 an acrylic, a vinyl acetate-based and vinyl ether-based adhesive agent are generally used for the adhesive layer of the tape preparation in addition to the rubber-based adhesion agent. Of these adhesive agents, the acrylic adhesive agent that does not require addition of an
25 antioxidant and a tackifier is preferably used. However, a polyester film or the like substantially having no permeability is used as the substrate for the tape preparation to improve the cutaneous absorption of the drug at the cost of the moisture dissipation of the skin.

30 Furthermore, a sorbitan ester is known to have the effect of promoting cutaneous absorption of a drug, and a poultice and a cream agent in which an alcohol and a sorbitan ester are used in combination have been proposed (Japanese Unexamined Patent Publication (Kokai) No. 61-
35 12621, Japanese Patent Publication No. 2604097, Japanese Unexamined Patent Publication (Kokai) No. 63-104913 and Japanese Unexamined Patent Publication (Kokai) No. 63-

230640). Moreover, a tape preparation in which an acrylic adhesive agent is allowed to contain a sorbitan ester has also been disclosed (Japanese Unexamined Patent Publication (Kokai) Nos. 1-233212, 1-233213, 2-196714 and 2-233617). However, a nonpermeable polyethylene terephthalate film or the like has been used as the substrates of these known tape preparations, and permeability necessary for the preparations is not ensured. It is clear from the explanation above that a tape preparation containing an oily adhesive agent composition showing high permeability, high cutaneous absorbability and high cohesive force has not been known.

Disclosure of the Invention

An object of the present invention is to provide: an adhesive agent composition which has firm adhesion to the human skin, high cohesive force, suitable permeability and practically adequate medicinal adaptability to a cutaneously absorbable drug and which shows no stimulation or extremely little stimulation of the human skin; a permeable adhesive tape which has an adhesive layer containing the adhesive agent composition and consequently showing high cohesive force, which produces no or an extremely decreased partial retention of the adhesive layer and which has high permeability; an adhesive drug composition which contains the adhesive agent composition and a drug, particularly a cutaneously absorbable drug; and an adhesive tape preparation which has a drug adhesive layer containing the adhesive drug composition and having high cohesive force, which produces no or an extremely decreased partial retention of the adhesive layer and which has high permeability

The object is achieved by the invention described below.

An adhesive agent composition of the present invention comprises 50 to 90% by weight of an acrylic adhesive agent, 2.5 to 50% by weight of a polyhydric

alcohol-containing liquid component, and 0.01 to 10% by weight of an aliphatic acid metal salt formed from an aliphatic acid that has a hydrocarbon group containing from 8 to 18 carbon atoms and a mono- to tri-valence metal.

A permeable adhesive tape of the present invention comprises a substrate and an adhesive layer formed on one side of the substrate and containing the adhesive agent composition of the invention.

An adhesive drug composition of the present invention comprises the adhesive agent composition of the invention and 0.05 to 40% by weight of a drug based on the weight of the adhesive agent composition.

An adhesive tape preparation of the present invention comprises a substrate and an adhesive drug layer formed on one side of the substrate and containing the adhesive drug composition of the invention.

Best Mode for Carrying Out the Invention

The adhesive agent composition of the present invention comprises 50 to 90 parts by weight of an acrylic adhesive agent, 2.5 to 50 parts by weight of a polyhydric alcohol-containing liquid component, 0.01 to 10 parts by weight of an aliphatic acid metal salt formed from an aliphatic acid that has a hydrocarbon group of 8 to 15 carbon atoms and a mono- to tri-valence metal.

The acrylic adhesive agent preferably contains at least one polymer selected from the group consisting of homopolymers of acrylic acid, methacrylic acid, an alkyl acrylate and an alkyl methacrylate, and copolymers containing at least one of the above monomer components. In the above copolymers, examples of an ethylene type unsaturated comonomer that copolymerizes with at least one monomer selected from the group consisting of acrylic acid, methacrylic acid, an alkyl acrylate and an alkyl methacrylate preferably include: hydroxyl group-containing monomers such as vinyl alcohol, 2-

hydroxy(meth)acrylate and hydroxypropyl (meth)acrylate;
carboxyl group-containing monomers such as (meth)acrylic
acid, itaconic acid, crotonic acid, maleic acid, maleic
anhydride and fumaric acid; sulfoxyl group-containing
5 monomers such as styrenesulfonic acid, allylsulfonic
acid, sulfopropyl acrylate, (meth)acryloyloxy-
naphthenesulfonic acid, (meth)acrylamidomethylpropane-
sulfonic acid and acryloyloxybenzenesulfonic acid; amino
group-containing monomers such as dimethylaminoethyl
10 acrylate and vinylpyrrolidone; hydroxyl group-containing
monomers such as hydroxyethyl (meth)acrylate and
hydroxypropyl (meth)acrylate; amide group-containing
acrylic monomers such as (meth)acrylamide,
dimethyl(meth)acrylamide, N-butyl(meth)acrylamide,
15 tetramethylbutyl(meth)acrylamide, N-
methylol(meth)acrylamide and
ethoxymethyl(meth)acrylamide; alkylaminoalkyl group-
containing acrylic monomers such as aminoethyl
(meth)acrylate, dimethylaminoethyl (meth)acrylate,
20 diethylaminoethyl (meth)acrylate and tert-butyl
(meth)acrylate; alkoxy group- (or ether bond-) containing
monomers (the ether bond being in the side chain) such as
methoxyethyl (meth)acrylate, ethoxyethyl (meth)acrylate,
butoxyethyl (meth)acrylate, tetrahydrofurfuryl
25 (meth)acrylate, methoxyethylene glycol (meth)acrylate,
methoxydiethylene glycol (meth)acrylate,
methoxypolyethylene glycol (meth)acrylate and
methoxypolypropylene glycol (meth)acrylate; saccharide
chain-containing monomers such as glycosyloxyethyl
30 (meth)acrylate, galactosyloxyethyl (meth)acrylate,
manosyloxyethyl (meth)acrylate and trehalosyloxyethyl
(meth)acrylate; vinyl-based monomers such as N-
(meth)acryloylamino acid; acrylic monomers such as a
urethane ester of acrylic acid, a urea ester and an
35 isocyanate ester; and vinyl-based monomers such as
(meth)acrylonitrile, vinyl acetate, vinyl propionate,
vinyl chloride, vinylpyrrolidone, vinylpyridine,

vinylpyrazine, vinylpiperazine, vinylpiperidone,
vinylpyrimidine, vinylpyrrole, vinylimidazole,
vinylcaprolactam, vinylloxazole, vinylthiazole,
vinylmorpholine, styrene, α -methylstyrene and bis(N,N-
5 dimethylaminoethyl) maleate. These comonomers are
copolymerized in the acrylic copolymers preferably in a
content of 2 to 60% by weight, more preferably 5 to 50%
by weight. When the content of the comonomers fall
outside the above range, acrylic copolymers showing a
10 satisfactory adhesive strength and a satisfactory
cohesive force sometimes cannot be obtained.

Furthermore, the adhesive agent contained in the
adhesive agent composition of the present invention is
preferably variously selected in accordance with the type
15 of the drug mixed with the adhesive agent so that the
drug is decomposed as little as possible. In general,
the mixing amount of the acrylic adhesive agent in the
adhesive agent composition, particularly in the drug
composition can be decreased by using a copolymer with a
20 comonomer having such a reactive functional group which
is generally considered to be highly reactive as a
carboxyl group, an amino group or an acid amide group.
Moreover, masking the reactive functional group can lower
the reactivity of the copolymer.

25 The adhesive agent composition of the present
invention contains the acrylic adhesive agent in a
content of 50 to 90% by weight, preferably 70 to 90% by
weight.

When the content of the acrylic adhesive agent is
30 less than 50% by weight, the cohesive force of the
adhesive agent composition thus obtained inconveniently
becomes insufficient. When the content exceeds 90% by
weight, the adhesive agent composition thus obtained
becomes viscous, and affixing the adhesive tape thus
35 obtained to a patient inconveniently gives an unpleasant
feeling.

The adhesive agent composition of the present

invention contains a polyhydric alcohol-containing liquid component. The polyhydric alcohol-containing liquid component contains at least one polyhydric alcohol. The content is preferably from 1 to 30% by weight, more preferably from 7.5 to 20% by weight based on the weight of the entire adhesive agent composition.

Preferred examples of the polyhydric alcohol contained in the polyhydric alcohol-containing liquid component include glycerin, propylene glycol, 1,3-butylene glycol, diglycerin, dipropylene glycol, 1,2,6-hexanetriol, sorbitol polyethylene glycol and pentaerythritol. These polyhydric alcohols show the effect of enhancing the effect of an aliphatic acid metal salt added to the adhesive agent composition of the present invention as an improver of the cohesive force. The content of the polyhydric alcohol is preferably from 7.5 to 50% by weight based on the weight of the adhesive agent composition. When the content of the polyhydric alcohol is less than 7.5% by weight, the cutaneous absorption of a drug that is incorporated into the adhesive agent composition thus obtained sometimes becomes insufficient. When the content exceeds 50% by weight, the cohesive force of the adhesive agent composition sometimes become insufficient. As a result, the adhesive agent layer sometimes remains on the skin when the tape preparation is peeled off.

The above polyhydric alcohol-containing liquid component may contain at least one substance selected from the group consisting of sorbitan esters, aliphatic esters other than the sorbitan esters, and polyvinylpyrrolidone, in addition to the above polyhydric alcohols. Sorbitan esters, aliphatic esters different from the sorbitan esters, and polyvinylpyrrolidone in combination with the polyhydric alcohols act to promote cutaneous absorption of the drug contained in the adhesive agent composition or drug composition.

Sorbitan esters used in the present invention are

preferably selected from sorbitan esters and poly(oxyalkylene)sorbitan esters of an aliphatic acid having a hydrocarbon group of 12 to 18 carbon atoms.

5 Sorbitan esters used in the present invention are selected from, for example, sorbitan monolaurate, sorbitan monopalmitate, sorbitan monostearate, sorbitan monooleate, sorbitan trioleate, poly(oxyethylene)sorbitan monolaurate, poly(oxyethylene)sorbitan monopalmitate, poly(oxyethylene)sorbitan monostearate,
10 poly(oxyethylene)sorbitan monooleate, poly(oxyethylene)sorbitan trioleate and the like. Of these sorbitan esters, sorbitan monolaurate, sorbitan monooleate, sorbitan trioleate, poly(oxyethylene)sorbitan monolaurate, poly(oxyethylene)sorbitan monopalmitate and
15 poly(oxyethylene)sorbitan monostearate are preferably used for cutaneous absorption tape preparations that show high drug permeability under a high permeability condition.

20 The content of a sorbitan ester in the polyhydric alcohol-containing liquid component is preferably from 0.5 to 20% by weight, more preferably from 1 to 10% by weight based on the weight of the entire adhesive agent composition. When the content of the sorbitan ester is less than 0.5% by weight and the adhesive agent
25 composition contains a drug, the effect of improving cutaneous absorption of the drug becomes inadequate. When the content exceeds 20% by weight, the adhesive agent composition thus obtained shows insufficient self-cohesive force, and part of the adhesive layer sometimes
30 remains on the skin after peeling the adhesive tape or tape preparation off the skin.

Aliphatic esters (different from the sorbitan esters) contained in the polyhydric alcohol-containing liquid component are preferably selected from isopropyl
35 myristate, isopropyl palmitate, isooctyl palmitate, ethyl oleate and diethyl sebacate and the like. Of these aliphatic esters, isopropyl myristate and/or isooctyl

palmitate is preferably used. The content of such a higher aliphatic ester is preferably from 1 to 30% by weight, more preferably from 5 to 20% by weight based on the weight of the entire adhesive agent composition.

5 When the content of an aliphatic ester is less than 1% by weight and the adhesive agent composition contains a drug, the effect of improving cutaneous absorption of the drug sometimes becomes inadequate. When the content exceeds 30% by weight, the adhesive agent composition
10 shows an insufficient self-agglomerating capacity, and part of the adhesive agent layer sometimes remains on the skin after peeling the adhesive tape preparation off the skin.

When the polyhydric alcohol-containing liquid
15 component contains polyvinylpyrrolidone, the content is preferably from 3 to 20% by weight, more preferably from 5 to 10% by weight based on the weight of the entire composition. When the content exceeds 20% by weight, the adhesive agent composition thus obtained shows an
20 insufficient self-agglomerating capacity, and part of the adhesive layer sometimes remains on the skin after peeling the adhesive tape or adhesive tape preparation off the skin. When the content is less than 3% by weight and the adhesive agent composition thus obtained contains
25 a drug, the effect of improving cutaneous absorption of the drug sometimes becomes inadequate.

In the polyhydric alcohol-containing liquid component used in the present invention, combined use of a sorbitan ester and an aliphatic ester different from
30 the sorbitan ester and/or polyvinylpyrrolidone, in particular, use of an aliphatic ester in combination can more enhance the cutaneous absorbability of a drug contained in the adhesive agent composition. The total content of the sorbitan ester, and the aliphatic ester
35 and/or polyvinylpyrrolidone used in combination therewith is then preferably from 10 to 40% by weight based on the weight of the entire adhesive agent composition.

The adhesive agent composition of the present invention contains an aliphatic acid metal salt formed from an aliphatic acid having a hydrocarbon group of 8 to 18 carbon atoms and a mono- to tri-valence metal. The aliphatic acid metal salt is effective in enhancing the cohesive force of the adhesive agent composition. Preferably, a salt of an aliphatic acid of 8 to 18 carbon atoms, for example, an aliphatic acid selected from caprylic acid, lauric acid, myristic acid, stearic acid and oleic acid with a metal selected from an alkali metal (e.g., sodium), an alkaline earth metal (e.g., magnesium), zinc and aluminum is employed.

The aliphatic acid metal salt used in the present invention is selected from, for example, sodium caprylate, sodium laurate, sodium myristate, sodium stearate, sodium oleate, magnesium stearate, zinc stearate, aluminum stearate and the like. Moreover, use of the aliphatic acid metal salt in combination with the above polyhydric alcohol can further improve the cohesive force of the adhesive agent composition. The mixing amount of the aliphatic acid metal salt is preferably from 0.01 to 10% by weight, more preferably from 0.1 to 5% by weight based on the weight of the entire adhesive composition. When the content of the aliphatic acid metal salt is less than 0.1% by weight, the adhesive agent composition thus obtained shows an insufficient cohesive force. Moreover, when the content is at least 10% by weight, excessive gelation takes place in the adhesive agent composition thus obtained, and handling of the composition becomes difficult. Furthermore, when a drug is incorporated into the adhesive agent composition, the aliphatic acid metal salt does not influence the cutaneous absorption of the drug.

The permeable adhesive tape of the present invention is prepared by forming an adhesive layer containing the adhesive agent composition of the present invention on one side of a substrate.

The substrate used for the permeable adhesive tape of the present invention preferably has air permeability and permeability; however, it preferably permits no transfer (transmission, diffusion, etc.) of a chemical drug, particularly no transfer of a medicine. The following materials can be used as a substrate that prevents a drug from transferring: a plastic film or porous film composed of polyethylene-based, polypropylene-based, polyester-based, polyamide-based, polytetrafluoroethylene-based, polyvinyl chloride-based or polyurethane-based polymer; and an unwoven fabric, a knitted fabric or a woven fabric prepared from a fiber formed from any of these polymers. The above porous film, or the above unwoven fabric, knitted fabric or woven fabric has good air permeability, permeability and flexibility, and is a substrate effective in preventing stimulation of the skin.

The permeability of the adhesive tape of the present invention is preferably at least $300 \text{ g/m}^2 \cdot \text{day}$, more preferably from 600 to $800 \text{ g/m}^2 \cdot \text{day}$.

The adhesive layer of the adhesive tape of the present invention preferably has a thickness of 5 to $1,000 \text{ }\mu\text{m}$, more preferably 10 to $500 \text{ }\mu\text{m}$.

The adhesive tape of the present invention can be produced by forming an adhesive layer containing the adhesive agent composition of the present invention on one side of the substrate by hot melt coating, emulsion coating or solvent coating. Of these coating methods, the solvent coating method is preferably used. The solvent coating method is conducted in the following manner: an adhesive agent composition is dissolved in a low boiling point solvent (preferably having a boiling point up to 80°C) such as ethyl acetate to give a dope for coating, and a substrate is coated with the dope on one side and dried to form an adhesive layer; alternatively, a releasing material is coated with the dope on one side, and the coating layer is dried,

followed by joining the coating adhesive layer on the releasing material to the substrate.

Examples of the solvent used for the preparation of the dope include ethyl acetate, chloroform, methylene chloride, cyclohexane and tetrahydrofuran. Of these solvents, ethyl acetate is preferably used. Moreover, a solvent mixture of ethyl acetate and alcohol is preferably used because it prevents gelation of when an aliphatic acid metal salt is added.

Moreover, examples of the releasing material include a metal foil coated with a release agent such as silicone and fluorine, and a film of plastics such as polyester, polyolefin, cellulose ester and polyamide. The releasing material is used to protect the adhesive layer surface of the adhesive tape until the tape is used.

The adhesive drug composition of the present invention contains the above adhesive agent composition of the present invention and a drug in an amount of 0.05 to 40% by weight, preferably 5 to 10% by weight based on the weight of the adhesive agent composition. When the content of the drug is less than 0.05% by weight, the drug composition thus obtained cannot show the desired effect of the added drug. Moreover, when the content of the drug exceeds 40% by weight, the drug composition thus obtained shows insufficient adhesion.

Drugs used for the adhesive drug composition include one or more pharmacologically active substances such as nonsteroidal anti-inflammatory agents, antihypertensives, local anesthetics, antibiotics, calcium antagonists, cardiotonics, antiepileptics, hypotensive diuretics, antifungals, antiallergics, antihistaminics, anti-cancer agents, antipsychotics, antivertigo agents, sleep controlling agents, coronary vasodilators, hormones, hypotensors, treating agents for asthma and nositis, hypoglycemics and antiulcer agents.

Typical examples of the drugs are shown below.

1) Nonsteroidal anti-inflammatory agents including

acetylsalicylic acid, methyl salicylate, indomethacin, diclofenac, ibuprofen, ketoprofen, flurbiprofen, mefenamic acid, phenylbutazone, aminopyrin, piroxicam and felbinac.

5 2) Antihypertensives including pindolol, atenolol, propanolol, nadolol, ajmaline, alprenolol hydrochloride, metoprolol tartrate, quinidine sulfate, timolol maleate and disopyramide.

10 3) Local anesthetics including tetracaine, procaine, benzocaine and lidocaine.

 4) Antibiotics including chloramphenicol and tetracycline.

 5) Calcium antagonists including nifedipine and nicardipine.

15 6) Cardiotonics including dopamine hydrochloride and digitalis.

 7) Antiepileptics including sodium valproate and phenytoin.

20 8) Hypotensive diuretics including hydrochlorothiazide.

 9) Antifungals including griseofulvin and amphotericin B.

25 10) Antiallergics•antihistaminics including cycloheptadine hydrochloride, diphenhydramine hydrochloride, mequitazine and phenbenzamine.

 11) Anti-cancer agents including 5-fluorouracil and mitomycin C.

30 12) Antipsychotropics including etizolam, maprotiline hydrochloride, amitriptyline hydrochloride, mianserin hydrochloride and diazepam.

 13) Antivertigo agents including scopolamine.

 14) Sleep controlling agents including amobarbital and phenobarbital.

35 15) Coronary vasodilators including dipyridamol, diltiazem, isosorbide nitrate, nifedipine, nitroglycerin and pentaerythritol tetranitrate.

 16) Hormones including estradiol, estrogen,

testosterone, progesterone and prostaglandin.

17) Hypotensors including clonidine hydrochloride,
plazosin hydrochloride, guanfacine hydrochloride,
bunazosin hydrochloride, arotinolol hydrochloride,
5 bunitrolol hydrochloride, penbutolol sulfate, guanabenz
acetate and eranapuril maleate

18) Treating agents for asthma and nositis
including azelastin hydrochloride, cromoglicic acid and
ketotifen fumarate.

10 19) Hypoglycemics including gliclazide and
glibenclamid.

20) Antiulcer agents including glycopyrronium
bromide, famotidine and clebopride malate.

At least two of the above drugs can be used in
15 combination in accordance with the object and action of
the medicinal treatment.

For the adhesive drug composition of the present
invention, the cohesive force of the composition can be
improved without lowering the cutaneous absorbability of
20 the drug by using an adhesive agent composition in which
the polyhydric alcohol-containing liquid component and
aliphatic acid metal salt are mixed with the acrylic
adhesive agent.

The adhesive tape preparation of the present
25 invention is produced by forming an adhesive drug layer
containing the adhesive drug composition of the present
invention on one side of a substrate.

The substrate of the adhesive tape preparation of
the present invention can be selected from a material
30 similar to the substrate of the permeable adhesive tape
in the present invention. Moreover, the adhesive drug
layer can be formed from the adhesive drug composition of
the present invention in the same manner as in the
formation of the adhesive layer in the production of the
35 permeable adhesive tape.

For the adhesive tape preparation of the present
invention, the permeability is preferably at least 300

g/m²·day, more preferably from 600 to 800 g/m²·day.

Furthermore, for the adhesive tape preparation of the present invention, the thickness of the adhesive drug layer is preferably from 5 to 1,000 μm, more preferably from 10 to 500 μm. The adhesive drug layer in the adhesive tape preparation of the present invention contains the adhesive composition of the present invention in combination with a drug. As a result, the adhesive drug layer can show good cutaneous absorption of the drug as well as good air permeability and permeability.

Examples

The present invention will be further explained below by making reference to examples. In the examples, the cutaneous absorption test of a drug in an adhesive tape preparation, the cohesive force test, peeling test and permeability measurement test of an adhesive layer or adhesive drug layer were conducted by the following procedures.

(1) Cutaneous Absorption Test of Drugs

Back skin of a YMP (Yucatan Micro Pig: female, 20 kg) to which a dermal external drug composition (0.4 cm² x 0.4 cm²) was affixed was mounted on the upper portion of a vertical diffusion cell. In the lower portion of the cell was placed 10 ml of a phosphoric acid buffer (pH = 7.4, containing 1% of sodium dodecylsulfate when estradiol was used), and stirred for 24 hours (48 hours when estradiol was used). The phosphoric acid buffer was sampled from the lower portion of the cell after stirring, and the concentration of the drug transferred to the buffer in the lower portion of the cell was quantitatively determined by liquid chromatography.

(2) Cohesive Force Test

The adhesive layer or adhesive drug layer of an adhesive tape or adhesive tape preparation containing a

sample adhesive agent composition or adhesive drug composition was affixed to a Bakelite plate. The tape was then peeled off, and the presence or absence of the adhesive layer or adhesive drug layer on the Bakelite plate surface was visually judged in accordance with the following criteria: good (no adhesion retention of the adhesive layer or adhesive drug layer); and poor (adhesion retention thereof).

(3) Peeling Test

The adhesive layer of a sample adhesive tape 12 mm wide or the adhesive drug layer of a sample adhesive tape preparation 12 mm wide was affixed to a Bakelite plate surface. A load of 300 g/cm² was applied to the tape or tape preparation to allow it to adhere thereto. One end of the sample adhesive tape or adhesive tape preparation was then peeled off the plate at a peeling rate of 300 mm/min at a peel angle of 180°, and the peeling strength was measured.

(4) Permeability Test

In a glass weighing bottle having an inside diameter of 38 mm was placed 26 g of calcium chloride. An adhesive layer, an adhesive drug layer or a support allowed to adhere to a gauze having a permeability of 11,000 g/m²·day was then fixed to the upper portion of the bottle. The bottle was then left in a thermohygrostat at 40°C at a relative humidity of 70% for 3 hours. The moisture content permeated through the specimen per square meter per 24 hours was calculated from the increased mass of the contents of the test weighing bottle. The permeability of the adhesive layer, adhesive drug layer or support was represented by the measured value thus obtained.

Materials used in the examples will be described below.

(1) Ketoprofen and felbinac used in the present examples were obtained from Sigma Chemical. Estradiol and testosterone were obtained from TOKYO KASEI ORGANIC

CHEMICAL. All the following compounds were obtained from Kanto Chemical Co., Inc.: glycerin (GC), 1,2,6-hexanetriol, isopropyl myristate (IPM), isooctyl palmitate (IOP), ethyl oleate (OE), magnesium stearate (StMg), sorbitan monolaurate (SPAN20), sorbitan monooleate (SPAN80), sorbitan trioleate (SPAN85), poly(oxyethylene)sorbitan monolaurate (TWEEN20), poly(oxyethylene)sorbitan monopalmitate (TWEEN40), poly(oxyethylene)sorbitan monostearate (TWEEN60) and polyvinylpyrrolidone (PVP).

(2) The pig skin used in the permeation experiment was obtained from Charles River.

(3) A permeable woven fabric composed of polyethylene terephthalate was used as the substrate. MOHRUS TAPE (trade name, manufactured by Hisamitsu Pharmaceutical Co. Inc.) and Cell Touch (trade name, manufactured by Takeda Chemical Industries Ltd.) were used as reference samples. MOHRUS TAPE was a tape preparation having an adhesive layer which contains ketoprofen as a drug and for which a rubber-based adhesive agent was used, and showing no permeability. Moreover, Cell Touch was a poultice containing felbinac as a drug.

Two polyhydric alcohols were used in Examples 1, 2 to be explained below, and the cohesive force was examined. Systems in which an aliphatic acid metal salt was used or no polyhydric alcohol was used were selected in Comparative Examples 1 to 6. MOHRUS TAPE was used in Reference Example 1, and the results were compared and examined.

Example 1

To 9.3 g of an acrylic adhesive agent (an acrylic adhesive agent obtained by copolymerizing the three components composed of 7% by weight of methyl acrylate, 90% by weight of 2-ethylhexyl acrylate and 3% by weight of acrylic acid; a dope-like material prepared by dissolving the adhesive agent in ethyl acetate and

containing 21.6% of the agent was used) were added 2.0 g of glycerin and 0.04 g of magnesium stearate; an ethyl acetate-ethanol mixture solution (ethyl acetate/ethanol volume ratio of 2/1) was further added in an amount of 45 ml. The mixture was stirred with a homogenizer to give a coating liquid for an adhesive layer. A PET film treated with silicone was coated with the coating liquid by a doctor knife to form a coating layer (50 μ m thick after drying), which was dried at 60°C for 30 minutes to form an adhesive layer 50 μ m thick. The adhesive tape thus obtained was used in the cohesive force test and peeling test. The adhesive layer of the adhesive tape contained 49% by weight of the acrylic adhesive agent, 50% by weight of glycerin and 1% by weight of magnesium stearate. Table 1 shows the test results.

Example 2

An adhesive tape was produced in the same manner as in Example 1 except that 1,2,6-hexanetriol was used in place of glycerin.

Table 1 shows the test results.

Comparative Example 1

An adhesive tape was produced in the same manner as in Example 1 except that the adhesive agent composition (coating liquid) was prepared in such a manner that the adhesive layer obtained after drying comprised 50% by weight of an acrylic adhesive agent and 50% by weight of glycerin.

Table 1 shows the test results.

Comparative Example 2

An adhesive tape was produced in the same manner as in Example 1 except that the adhesive agent composition (coating liquid) was prepared in such a manner that the adhesive layer thus obtained comprised 49.95% by weight of an acrylic adhesive agent, 50% by weight of glycerin and 0.05% by weight of magnesium stearate.

Table 1 shows the test results.

Comparative Example 3

5 An adhesive tape was produced in the same manner as in Example 1 except that the adhesive agent composition (coating liquid) was prepared in such a manner that the adhesive layer thus obtained comprised 45% by weight of an acrylic adhesive agent, 50% by weight of glycerin and 5% by weight of magnesium stearate.

Table 1 shows the test results.

Comparative Example 4

10 An adhesive tape was produced in the same manner as in Example 1 except that the adhesive composition (coating liquid) was prepared in such a manner that the adhesive layer thus obtained comprised 49% by weight of an acrylic adhesive agent, 50% by weight of isopropyl myristate and 1% by weight of magnesium stearate.

Table 1 shows the test results.

Comparative Example 5

20 An adhesive tape was produced in the same manner as in Comparative Example 4 except that isooctyl palmitate was used in place of isopropyl myristate.

Table 1 shows the test results.

Comparative Example 6

25 An adhesive tape was produced in the same manner as in Comparative Example 4 except that oleic acid was used in place of isopropyl myristate.

Table 1 shows the test results.

Reference Example 1

MOHRUS TAPE was used in the same tests as in Example 1.

30 Table 1 shows the test results.

Table 1

	Adhesive agent composition			Cohesive force of an adhesive layer (prevention of adhesion retention of adhesive drug layer)	Peeling strength (gf)
	Acrylic adhesive agent (wt.%)	Polyhydric alcohol-containing liquid component (wt.%)	Aliphatic acid salt (wt.%)		
Ex. 1	49	GC 50	StMg 1	good	2.22×10^2
Ex. 2	49	1,2,6-hexanetriol 50	StMg 1	good	2.38×10^2
Comp. Ex. 1	50	GC 50	-	poor	-
Comp. Ex. 2	49.95	GC 50	StMg 0.05	poor	-
Comp. Ex. 3	45	GC 50	StMg 5	coating being impossible	-
Comp. Ex. 4	49	IPM 50	StMg 1	poor	-
Comp. Ex. 5	49	IOP 50	StMg 1	poor	-
Comp. Ex. 6	49	OA 50	StMg 1	poor	-
Ref. Ex. 1	-	-	-	good	1.98×10^2

Note: GC = glycerin
 StMg = magnesium stearate
 IPM = isopropyl myristate
 IOP = isooctyl palmitate
 OA = oleic acid
 Coating being impossible = Gelation of the coating liquid took place, and conducting coating was impossible because handling became impossible during preparation of the adhesive agent.

In Examples 3 to 8, adhesive agents containing ketoprofen as a pharmacologically active substance were used, and the effects of six aliphatic acid metal salts on the improvement of the cohesive force were investigated. Moreover, aliphatic esters were added as liquid components in Examples 9, 10 in addition to a polyhydric alcohol, and their influence on the cohesive force was investigated. In comparative Examples 7, 8, investigations were carried out on a system in which either an aliphatic acid metal salt or a polyhydric alcohol was not used, and a system in which ethyl acetoacetate aluminum diisopropionate was used.

Example 3

An adhesive tape was produced in the same manner as in Example 1 except that the adhesive layer subsequent to drying was an adhesive drug layer composed of an adhesive drug composition comprising 43% by weight of the acrylic adhesive agent, 50% by weight of glycerin, 1% by weight of magnesium stearate and 6% by weight of ketoprofen. An adhesive tape preparation was thus obtained.

Table 2 shows the test results.

Example 4

5 An adhesive tape preparation was produced in the same manner as in Example 3 except that sodium caprylate was used in place of magnesium stearate.

Table 2 shows the test results.

Example 5

10 An adhesive tape preparation was produced in the same manner as in Example 3 except that sodium laurate was used in place of magnesium stearate.

Table 2 shows the test results.

Example 6

15 An adhesive tape preparation was produced in the same manner as in Example 3 except that sodium stearate was used in place of magnesium stearate.

Table 2 shows the test results.

Example 7

20 An adhesive tape preparation was produced in the same manner as in Example 3 except that zinc stearate was used in place of magnesium stearate.

Table 2 shows the test results.

Example 8

25 An adhesive tape preparation was produced in the same manner as in Example 3 except that aluminum stearate was used in place of magnesium stearate.

Table 2 shows the test results.

Example 9

30 An adhesive tape was produced in the same manner as in Example 1 except that the adhesive layer subsequent to drying was an adhesive drug layer composed of an adhesive drug composition comprising 43% by weight of the acrylic adhesive agent, 10% by weight of sorbitan monolaurate, 40% by weight of glycerin, 1% by weight of magnesium stearate and 6% by weight of ketoprofen to give an
35 adhesive tape preparation.

Table 2 shows the test results.

Example 10

An adhesive tape was produced in the same manner as in Example 1 except that the adhesive layer subsequent to drying was an adhesive drug layer composed of an adhesive drug composition comprising 43% by weight of the acrylic adhesive agent, 10% by weight of sorbitan monolaurate, 20% by weight of isopropyl myristate, 20% by weight of glycerin, 1% by weight of magnesium stearate and 6% by weight of ketoprofen to give an adhesive tape preparation.

Table 2 shows the test results.

Comparative Example 7

An adhesive tape preparation was produced in the same manner as in Example 3 except that isopropyl myristate was used in place of glycerin.

Table 2 shows the test results.

Comparative Example 8

An adhesive tape preparation was produced in the same manner as in Example 3 except that sorbitan monolaurate was used in place of glycerin.

Table 2 shows the test results.

Comparative Example 9

An adhesive tape preparation was produced in the same manner as in Example 3 except that magnesium stearate was not used.

Table 2 shows the test results.

Comparative Example 10

An adhesive tape preparation was produced in the same manner as in Example 3 except that ethyl acetoacetate aluminum diisopropionate was used in place of magnesium stearate.

Table 2 shows the test results.

Table 2

	Composition of adhesive drug layer				Cohesive force (prevention of adhesion retention of adhesive drug layer)	Peeling strength (gf)
	Acrylic adhesive agent (wt.%)	Polyhydric alcohol-containing liquid component (wt.%)	Aliphatic acid salt (wt.%)	Drug (wt.%)		
Ex. 3	43	GC 50	StMg 1	KP 6	good	2.42×10^2
Ex. 4	43	GC 50	CpNa 1	KP 6	good	2.37×10^2
Ex. 5	43	GC 50	RuNa 1	KP 6	good	2.22×10^2
Ex. 6	43	GC 50	StNa 1	KP 6	good	2.51×10^2
Ex. 7	43	GC 50	StZn 1	KP 6	good	2.87×10^2
Ex. 8	43	GC 50	StAl 1	KP 6	good	2.61×10^2
Ex. 9	43	SPAN20 10 GC 40	StMg 1	KP 6	good	2.73×10^2
Ex. 10	43	SPAN20 10 IPM 50 GC 20	StMg 1	KP 6	good	2.69×10^2
Comp. Ex. 7	43	IPM 50	StMg 1	KP 6	poor	-
Comp. Ex. 8	43	SPAN20 50	StMg 1	KP 6	poor	-
Comp. Ex. 9	44	GC 50	-	KP 6	poor	-
Comp. Ex. 10	43	GC 50	Al 1	KP 6	poor	-

Note: GC = glycerin
 SPAN20 = sorbitan monolaurate
 IPM = isopropyl myristate
 StMg = magnesium stearate
 CpNa = sodium caprylate
 RuNa = sodium laurate
 StNa = sodium stearate
 StZn = zinc stearate
 StAl = aluminum stearate
 Al = ethyl acetoacetate aluminum diisopropionate
 KP = ketoprofen

The influence of an aliphatic acid metal salt on the cutaneous permeability of a drug was investigated in Example 11. The cutaneous permeability of a drug was investigated in a system without an aliphatic acid metal salt and in a system in which ethyl acetate aluminum diisopropionate was used as a metal chelate compound that has the possibility of showing a mutual action with the drug, in Comparative Examples 11, 12.

Example 11

To 15.3 g of an acrylic adhesive agent (an acrylic adhesive agent obtained by copolymerizing the three components composed of 7% by weight of methyl methacrylate, 90% by weight of 2-ethylhexyl acrylate and 3% by weight of acrylic acid; a dope-like material prepared by dissolving the adhesive agent in ethyl acetate and containing 21.6% of the agent was used) were added 0.1 g of sorbitan monolaurate, 0.3 g of glycerin,

0.24 g of ketoprofen and 0.04 g of magnesium stearate; an ethyl acetate-ethanol solution mixture (ethyl acetate/ethanol volume ratio of 2/1) was further added in an amount of 45 ml. The mixture was stirred with a homogenizer to give a coating liquid for an adhesive drug layer of an adhesive tape preparation.

A PET film treated with silicone was coated with the coating liquid by a doctor knife to form a coating layer (50 μ m thick after drying), which was dried at 60°C for 30 minutes to form an adhesive drug layer 50 μ m thick. The adhesive drug layer was affixed to an air permeable woven fabric composed of polyethylene terephthalate fiber, and subjected to the permeability test.

Table 3 shows the test results.

Comparative Example 11

An adhesive tape preparation was produced in the same manner as in Example 11 except that magnesium stearate was not used.

Table 3 shows the test results.

Comparative Example 12

An adhesive tape preparation was produced in the same manner as in Example 11 except that ethyl acetate aluminum diisopropionate was used in place of magnesium stearate.

Table 3 shows the test results.

Table 3

	Composition of adhesive drug layer				Cohesive force (prevention of adhesion retention of adhesive drug layer)	Cutaneous absorption amount of ketoprofen (mg/cm ² · 24 hr)
	Acrylic adhesive agent (wt.%)	Polyhydric alcohol-containing liquid component (wt.%)	Aliphatic acid salt (wt.%)	Drug (wt.%)		
Ex. 11	83	SPAN20 2.5 GC 7.5	StMg 1	KP 6	good	60
Comp. Ex. 11	84	SPAN20 2.5 GC 7.5	-	KP 6	poor	57
Comp. Ex. 12	83	SPAN20 2.5 GC 7.5	Al 1	KP 6	poor	21

Note: SPAN20 = sorbitan monolaurate
GC = glycerin
StMg = magnesium stearate
Al = ethyl acetoacetate aluminum diisopropionate
KP = ketoprofen

It has been confirmed from Table 3 that an aliphatic acid metal salt contained in an adhesive drug layer has the effect of improving the cohesive force of the adhesive drug layer without decreasing the cutaneous absorption of a drug.

In Examples 12 to 17 to be explained below, investigations on the absorption promoting effect of six absorbefaciants and the cohesive force and permeability of adhesive agents containing the absorbefaciants were carried out. In Comparative Examples 13 to 18, experiments were conducted either in a system in which an absorbefaciant was used or in a system in which no absorbefaciant was used, and the results were compared with those of Example 12 and studied. In Comparative Example 19, a comparative experiment was conducted in a system with or without an aliphatic acid, and the results were compared with those of Example 12. Moreover, in Reference Example 2, MOHRUS TAPE that was a tape preparation having no permeability was used, and the results were compared and investigated.

Example 12

To 15.3 g (83% by weight) of an acrylic adhesive agent (a 21.6% dope dissolved in ethyl acetate) obtained by copolymerizing the three components composed of 7% by weight of methyl methacrylate, 90% by weight of 2-ethylhexyl acrylate and 3% by weight of acrylic acid was added 45 ml of an ethyl acetate-ethanol solution mixture (ethyl acetate/ethanol volume ratio of 2/1). To the mixture were further added 0.1 g (2.5% by weight) of sorbitan monolaurate, 0.3 g (7.5% by weight) of glycerin, 0.24 g (6% by weight) of ketoprofen and 0.04 g (1% by weight) of magnesium stearate (StMg). The contents were stirred with a homogenizer to give a coating liquid for an adhesive drug layer of an adhesive tape preparation. A PET film treated with silicone was coated with the coating liquid by a doctor knife to form a coating layer (50 μ m thick after drying), which was dried at 60°C for

30 minutes to form an adhesive drug layer 50 μ m thick. The adhesive drug layer was affixed to an air permeable woven fabric composed of a polyethylene terephthalate fiber, and subjected to the cutaneous absorption test, cohesive force test and permeability test. Table 4 shows the test results.

Example 13

An adhesive tape preparation was produced in the same manner as in Example 12 except that sorbitan monooleate was used for the adhesive drug layer in place of sorbitan monolaurate.

Table 4 shows the test results.

Example 14

An adhesive tape preparation was produced in the same manner as in Example 12 except that sorbitan trioleate was used for the adhesive drug layer in place of sorbitan monolaurate.

Table 4 shows the test results.

Example 15

An adhesive tape preparation was produced in the same manner as in Example 12 except that poly(oxyethylene)sorbitan monolaurate was used for the adhesive drug layer in place of sorbitan monolaurate.

Table 4 shows the test results.

Example 16

An adhesive tape preparation was produced in the same manner as in Example 12 except that poly(oxyethylene)sorbitan monopalmitate was used for the adhesive drug layer in place of sorbitan monolaurate.

Table 4 shows the test results.

Example 17

An adhesive tape preparation was produced in the same manner as in Example 12 except that poly(oxyethylene)sorbitan monostearate was used for the adhesive drug layer in place of sorbitan monolaurate.

Table 4 shows the test results.

Comparative Example 13

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 17.2 g of an acrylic adhesive agent, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 93% by weight of the acrylic adhesive agent, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

Comparative Example 14

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 15.8 g of an acrylic adhesive agent, 0.3 g of glycerin, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 85.5% by weight of the acrylic adhesive agent, 7.5% by weight of glycerin, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

Comparative Example 15

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 13.5 g of an acrylic adhesive agent, 0.8 g of isopropyl myristate, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 73% by weight of the acrylic adhesive agent, 20% by weight of isopropyl myristate, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

Comparative Example 16

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 12.1 g of an acrylic adhesive agent, 0.3 g of glycerin, 0.8 g of isopropyl myristate, 0.24 g of ketoprofen and 0.04 g of

magnesium stearate, and that the dried adhesive drug layer was composed of 65.5% by weight of the acrylic adhesive agent, 7.5% by weight of glycerin, 20% by weight of isopropyl myristate, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

Comparative Example 17

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 15.8 g of an acrylic adhesive agent, 0.4 g of sorbitan monolaurate, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 83% by weight of the acrylic adhesive agent, 10% by weight of sorbitan monolaurate, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

Comparative Example 18

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 15.8 g of an acrylic adhesive agent, 0.4 g of poly(oxyethylene)sorbitan monolaurate, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 83% by weight of the acrylic adhesive agent, 10% by weight of poly(oxyethylene)sorbitan monolaurate, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

Comparative Example 19

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 15.6 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of glycerin and 0.24 g of ketoprofen, and that the dried adhesive drug layer was composed of 84% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan

monolaurate, 7.5% by weight of glycerin and 6% by weight of ketoprofen.

Table 4 shows the test results.

Reference Example 2

5 MOHRUS TAPE was subjected to the same tests as in Example 12. Table 4 shows the test results.

In Examples 18 to 19 to be explained below, the relationship between an addition amount of sorbitan monolaurate and a permeated amount of ketoprofen, and the
10 cohesive force and permeability of the adhesive drug layers containing the absorption promoters were investigated.

Example 18

An adhesive tape preparation was produced in the
15 same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 14.9 g of an acrylic adhesive agent, 0.2 g of sorbitan monolaurate, 0.3 g of glycerin, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug
20 layer was composed of 80.5% by weight of the acrylic adhesive agent, 5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

25 Example 19

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 13.9 g of an acrylic adhesive agent, 0.4 g of sorbitan monolaurate,
30 0.3 g of glycerin, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 75.5% by weight of the acrylic adhesive agent, 10% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 6% by weight of ketoprofen
35 and 1% by weight of magnesium stearate.

Table 4 shows the test results.

In Example 20 to be explained below, the

relationship (compared with Example 12) between an addition amount of glycerin and a permeated amount of ketoprofen, and the cohesive force and permeability of an adhesive drug layer containing the absorption promoter were investigated.

Example 20

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 13.9 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.6 g of glycerin, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 75.5% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 15% by weight of glycerin, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

In Examples 21 to 22 to be explained below, the relationship between an addition amount of isopropyl myristate and a permeated amount of ketoprofen, and the cohesive force and permeability of an adhesive drug layer containing the absorption promoter were investigated.

Example 21

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 13.5 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of glycerin, 0.4 g of isopropyl myristate, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 73% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 10% by weight of isopropyl myristate, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

Example 22

An adhesive tape preparation was produced in the

same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 11.7 g of an acrylic adhesive agent, 0.1 g of sorbitan laurate, 0.3 g of glycerin, 0.8 g of isopropyl myristate, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 63.5% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 20% by weight of isopropyl myristate, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

Comparative Example 20

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 13.5 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.4 g of isopropyl myristate, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 80.3% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 10% by weight of isopropyl myristate, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

In Examples 23 to 24 to be explained below, the permeability of ketoprofen, and the cohesive force and permeability of an adhesive drug layer containing the absorption promoter were investigated when 1,2,6-hexanetriol was used in place of glycerin and isooctyl palmitate was used in place of isooctyl myristate.

Example 23

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 15.3 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of 1,2,6-hexanetriol, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 83% by weight of the acrylic

adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of 1,2,6-hexanetriol, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

Table 4 shows the test results.

5 Example 24

10 An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 13.5 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of glycerin, 0.4 g of isooctyl palmitate, 0.24 g of ketoprofen and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 73% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 10% by weight of isooctyl palmitate, 6% by weight of ketoprofen and 1% by weight of magnesium stearate.

15 Table 4 shows the test results.

Table 4

	Additives	Permeated amount of ketoprofen ($\mu\text{g}/\text{cm}^2 \cdot 24 \text{ hr}$)	Cohesive force (prevention of adhesion retention of adhesive drug layer)	Permeability ($\text{g}/\text{m}^2 \cdot \text{day}$)
Ex. 12	Span20 2.5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	80	○	743
Ex. 13	Span80 2.5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	60	○	762
Ex. 14	Span85 2.5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	40	○	757
Ex. 15	TWEEN20 2.5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	53	○	498
Ex. 16	TWEEN40 2.5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	48	○	521
Ex. 17	TWEEN60 2.5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	42	○	512
Comp. Ex. 13	StMg 1.0 wt. %	24	○	504
Comp. Ex. 14	GC 7.5 wt. % StMg 1.0 wt. %	7	○	689
Comp. Ex. 15	IPM 20 wt. % StMg 1.0 wt. %	17	○	512
Comp. Ex. 16	GC 7.5 wt. % IPM 7.5 wt. % StMg 1.0 wt. %	20	○	677
Comp. Ex. 17	Span20 10 wt. % StMg 1.0 wt. %	60	X	457
Comp. Ex. 18	TWEEN20 10 wt. % StMg 1.0 wt. %	35	X	500
Comp. Ex. 19	Span20 2.5 wt. % GC 7.5 wt. %	82	X	722
Ref. Ex. 2	MOHRUS TAPE	40	○	0
Ex. 18	Span20 5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	132	○	738
Ex. 19	Span20 10 wt. % GC 7.5 wt. % StMg 1.0 wt. %	160	○	744

Table 4 (Continued)

	Additives	Permeated amount of ketoprofen ($\mu\text{g}/\text{cm}^2 \cdot 24 \text{ hr}$)	Cohesive force (prevention of adhesion retention of adhesive drug layer)	Permeability ($\text{g}/\text{m}^2 \cdot \text{day}$)
Ex. 20	Span20 2.5 wt.% GC 15 wt.% StMg 1.0 wt.%	100	○	787
Ex. 21	Span20 2.5 wt.% GC 7.5 wt.% IPM 10 wt.% StMg 1.0 wt.%	105	○	721
Ex. 22	Span20 2.5 wt.% GC 7.5 wt.% IPM 20 wt.% StMg 1.0 wt.%	121	○	761
Comp. Ex. 20	Span20 2.5 wt.% IPM 10 wt.% StMg 1.0 wt.%	78	X	743
Ex. 23	Span20 2.5 wt.% 1,2,6- hexanetriol 7.5 wt.% StMg 1.0 wt.%	70	○	744
Ex. 24	Span20 2.5 wt.% GC 7.5 wt.% IOP 10 wt.% StMg 1.0 wt.%	97	○	723

Note: SPAN20 = sorbitan monolaurate
SPAN80 = sorbitan monooleate
SPAN85 = sorbitan trioleate
GC = glycerin
StMg = magnesium stearate
TWEEN20 = poly(oxyethylene)sorbitan monolaurate
TWEEN40 = poly(oxyethylene)sorbitan monopalmitate
TWEEN60 = poly(oxyethylene)sorbitan monostearate
IPM = isopropyl myristate
IOP = isooctyl palmitate

In Example 25, felbinac was used as a nonsteroidal antiphlogistic analgesic in place of ketoprofen, and the permeability, and the cohesive force and permeability of an adhesive drug layer containing the medicine were investigated.

Example 25

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 16.4 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of glycerin, 0.04 g of felbinac and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 88.5% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 0.5% by weight of felbinac

and 1% by weight of magnesium stearate.

Table 5 shows the test results.

Reference Example 3

5 Cell Touch (trade name, poultice) was subjected to the same permeability test for felbinac and the same cohesive force test as in Example 25.

Table 5 shows the test results.

Table 5

	Additives	Permeated amount of felbinac ($\mu\text{g}/\text{cm}^2 \cdot 24 \text{ hr}$)	Cohesive force	Permeability ($\text{g}/\text{m}^2 \cdot \text{day}$)
Ex. 25	Span20 2.5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	4.2	good	722
Ref. Ex. 3	Cell Touch (trade name)	4.0	good	-

10 Note: SPAN20 = sorbitan monolaurate
GC = glycerin
StMg = magnesium stearate

15 Estradiol was used as a female sex hormone agent in Examples 26 to 27, to be explained below, and the permeability of estradiol of the adhesive drug layer, and the cohesive force and permeability of the adhesive drug layer containing the drug were investigated. Moreover, in order to achieve the high permeability of estradiol, 20 the same investigation was performed in Example 28, to be explained below, in a system in which ethyl oleate and polyvinylpyrrolidone were added.

Example 26

25 An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 14.0 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of glycerin, 0.128 g of estradiol and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 75.8% by weight of the acrylic 30 adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 3.2% by weight of estradiol and 1% by weight of magnesium stearate. Table 6 shows the test results.

Example 27

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 14.0 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of glycerin, 0.4 g of isopropyl myristate, 0.128 g of estradiol and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 75.8% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 10% by weight of isopropyl myristate, 3.2% by weight of estradiol and 1% by weight of magnesium stearate. Table 6 shows the test results.

Example 28

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 8.3 g of an acrylic adhesive agent, 0.2 g of sorbitan monolaurate, 0.4 g of isopropyl myristate, 0.6 g of 1,2,6-hexanetriol, 0.6 g of ethyl oleate, 0.24 g of polyvinylpyrrolidone, 0.16 g of estradiol and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 45% by weight of the acrylic adhesive agent, 5% by weight of sorbitan monolaurate, 10% by weight of isopropyl myristate, 15% by weight of 1,2,6-hexanetriol, 15% by weight of ethyl oleate, 6% by weight of polyvinylpyrrolidone, 4% by weight of estradiol and 1% by weight of magnesium stearate. Table 6 shows the test results.

Comparative Example 21

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 17.7 g of an acrylic adhesive agent, 0.128 g of estradiol and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 95.8% by weight of the acrylic adhesive agent, 3.2% by weight of estradiol and 1% by

weight of magnesium stearate. Table 6 shows the test results.

Table 6

	Additives	Permeated amount of estradiol ($\mu\text{g}/\text{cm}^2 \cdot 48 \text{ hr}$)	Cohesive force (prevention of adhesion retention of adhesive drug layer)	Permeability ($\text{g}/\text{m}^2 \cdot \text{day}$)
Ex. 26	Span20 2.5 wt. % GC 7.5 wt. % StMg 1.0 wt. %	20	○	724
Ex. 27	Span20 2.5 wt. % GC 2.5 wt. % IPM 10 wt. % StMg 1.0 wt. %	15.7	○	716
Ex. 28	Span20 5 wt. % IPM 10 wt. % 1,2,6- hexanetriol 15 wt. % OE 15 wt. % PVP 6 StMg - wt. %	35	○	720
Comp. Ex. 21	StMg 1.0 wt. %	1.1	○	515

Note: SPAN20 = sorbitan monolaurate
GC = glycerin
StMg = magnesium stearate
IPM = isopropyl myristate
OE = ethyl oleate
PVP = polyvinylpyrrolidone

Testosterone was used as a male sex hormone in Examples 29 to 30, to be explained below, and the permeability of the drug, and the cohesive force and permeability of the adhesive drug layer containing the drug were investigated.

Example 29

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 15.9 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of glycerin, 0.128 g of testosterone and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 85.8% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 3.2% by weight of testosterone and 1% by weight of magnesium stearate. Table 7 shows the test results.

Example 30

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 14.0 g of an acrylic adhesive agent, 0.1 g of sorbitan monolaurate, 0.3 g of glycerin, 0.4 g of isopropyl myristate, 0.128 g of testosterone and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 75.8% by weight of the acrylic adhesive agent, 2.5% by weight of sorbitan monolaurate, 7.5% by weight of glycerin, 10% by weight of isopropyl myristate, 3.2% by weight of testosterone and 1% by weight of magnesium stearate. Table 7 shows the test results.

Comparative Example 22

An adhesive tape preparation was produced in the same manner as in Example 12 except that the coating liquid for the adhesive drug layer contained 17.7 g of an acrylic adhesive agent, 0.128 g of testosterone and 0.04 g of magnesium stearate, and that the dried adhesive drug layer was composed of 95.8% by weight of the acrylic adhesive agent, 3.2% by weight of testosterone and 1% by weight of magnesium stearate. Table 7 shows the test results.

Table 7

	Additives		Permeated amount of testosterone ($\mu\text{g}/\text{cm}^2 \cdot 48 \text{ hr}$)	Cohesive force (prevention of adhesion retention of adhesive drug layer)	Permeability ($\text{g}/\text{m}^2 \cdot \text{day}$)
Ex. 29	Span20	2.5 wt. %	5.1	○	752
	GC	7.5 wt. %			
	StMg	1.0 wt. %			
Ex. 30	Span20	2.5 wt. %	6.2	○	734
	GC	7.5 wt. %			
	IPM	10 wt. %			
	StMg	1.0 wt. %			
Comp. Ex. 22	StMg	1.0 wt. %	2.5	○	485

Tables 2 to 7 show that the adhesive drug layer of the adhesive tape preparation in the present invention has good cohesive force (prevention of adhesion retention), peeling strength, permeability and the like.

Tables 3 to 7 show that the adhesive drug of the present invention has good permeability of the drug (cutaneous absorption).

5 Industrial Applicability

10 The adhesive agent composition and the adhesive tape of the present invention have good adhesion and permeability. Moreover, the adhesive drug composition and adhesive tape preparation of the present invention have good adhesion and permeability, and further shows good permeability of the drug (cutaneous absorption).
15 The effective drug can be subjected to cutaneous absorption without stimulation of the skin. Accordingly, the adhesive agent composition, adhesive tape, adhesive drug composition and adhesive tape preparation of the present invention can be industrially effectively utilized.

CLAIMS

1. (Amended) An adhesive agent composition comprising 50 to 90% by weight of an acrylic adhesive agent, 2.5 to 50% by weight of a polyhydric alcohol-containing liquid component, and 0.01 to 10% by weight of an aliphatic acid metal salt formed from an aliphatic acid that has a hydrocarbon group containing from 8 to 18 carbon atoms with a mono- to tri-valence metal, the polyhydric alcohol-containing liquid component containing, in addition to the polyhydric alcohol, at least one sorbitan ester compound selected from sorbitan esters and poly(oxyalkylene)sorbitan esters of aliphatic acids having a hydrocarbon group having 12 to 18 carbon atoms, in an amount of 0.5 to 20% by weight based on the total weight of the composition.

2. The adhesive agent composition according to claim 1, wherein the acrylic adhesive agent contains at least one polymer selected from the group consisting of homopolymers of acrylic acid, methacrylic acid, an alkyl acrylate and an alkyl methacrylate, and copolymers containing at least one of the above monomer components.

3. The adhesive agent composition according to claim 1, wherein the polyhydric alcohol-containing liquid component contains from 1 to 30% by weight of a polyhydric alcohol based on the weight of the entire composition.

4. The adhesive agent composition according to claim 1, wherein the polyhydric alcohol in the polyhydric alcohol-containing liquid component is selected from glycerin, propylene glycol, 1,3-butylene glycol, diglycerin, dipropylene glycol, 1,2,6-hexanetriol, sorbitol polyethylene glycol and pentaerythritol.

5. The adhesive agent composition according to claim 1, wherein the polyhydric alcohol-containing liquid component contains, in addition to the polyhydric alcohol and the sorbitan ester compound, at least one substance

selected from aliphatic esters different from the sorbitan ester compound and polyvinylpyrrolidone.

6. Cancelled

7. Cancelled

8. The adhesive agent composition according to claim 5, wherein the content of the aliphatic ester in the polyhydric alcohol-containing liquid component is from 1 to 30% by weight based on the total weight of the composition.

9. The adhesive agent composition according to claim 5, wherein the aliphatic ester is selected from isopropyl myristate, isopropyl palmitate, isooctyl palmitate, ethyl oleate and diethyl sebacate.

10. The adhesive agent composition according to claim 1, wherein in the aliphatic acid metal salt, the aliphatic acid having a hydrocarbon group containing 8 to 18 carbon atoms is selected from lauric acid, myristic acid, stearic acid and oleic acid, and the mono- to trivalent metal is selected from sodium, magnesium, zinc and aluminum.

11. (Amended) A permeable adhesive tape comprising a substrate and an adhesive layer formed on one side of the substrate and containing the adhesive agent composition according to any one of claims 1 to 5 and 8 to 10.

12. The permeable adhesive tape according to claim 11, wherein the permeable adhesive tape has a permeability of at least $300 \text{ g/m}^2 \cdot \text{day}$.

13. The permeable adhesive tape according to claim 11, wherein the adhesive layer has a thickness of 5 to $1,000 \text{ } \mu\text{m}$.

14. (Amended) An adhesive drug composition comprising the adhesive agent composition according to any one of claims 1 to 5 and 8 to 10, and 0.05 to 40% by weight of a drug based on the weight of the adhesive agent composition.

15. The adhesive drug composition according to claim 14, wherein the drug is selected from nonsteroidal anti-inflammatory agents, antihypertensives, local anesthetics, antibiotics, calcium antagonists,

ABSTRACT

5 The adhesive agent composition of the present invention comprises from 50 to 90% by weight of an acrylic adhesive agent, 2.5 to 50% by weight of a polyhydric alcohol-containing liquid component, and 0.01 to 10% by weight of a salt of a mono- to tri-valence metal of an aliphatic acid that contains a hydrocarbon group of 8 to 18 carbon atoms. The adhesive agent
10 composition shows good adhesion, cohesive force and permeability, and an adhesive drug composition having the above properties can be prepared by adding a drug (medicine, etc.) to the adhesive composition. An
15 adhesive tape excellent in permeability or an adhesive tape preparation excellent in permeability and cutaneous absorption of the drug can be produced by coating a substrate with the adhesive agent composition or adhesive drug composition.

Declaration and Power of Attorney for Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。

As a below named inventor, I hereby declare that:

私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。

My residence, post office address and citizenship are as stated next to my name.

下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者（下記の氏名が一つの場合）もしくは最初かつ共同発明者であると（下記の名称が複数の場合）信じています。

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

ADHESIVE AGENT COMPOSITION, AND
PERMEABLE ADHESIVE TAPE, ADHESIVE DRUG
COMPOSITION AND ADHESIVE TAPE
PREPARATION CONTAINING THE ADHESIVE
AGENT COMPOSITION

上記発明の明細書（下記の欄でx印がついていない場合は、本書に添付）は、

the specification of which is attached hereto unless the following box is checked:

☐ 月 日に提出され、米国出願番号または特許協定条約
国際出願番号を _____ とし、
(該当する場合) _____ に訂正されました。

☐ was filed on July 27, 1999
as United States Application Number or PCT
International Application Number PCT/JP99/04028
and was amended on April 21, 2000
[B2] _____ (if applicable) under PCT
Article 34

私は、特許請求範囲を含む上記訂正後の明細書を検討し、内容を理解していることをここに表明します。

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

私は、連邦規則法典第37編第1条56項に定義されるとおり、特許資格の有無について重要な情報を開示する義務があることを認めます。

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56.

Japanese Language Declaration

日本語宣言書

私は、米国法典第35編119条(a)-(d)項又は365条(b)項に基づき下記の、米国外の国の少なくとも一カ国を指定している特許協力条約365(a)項に基づく国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している、本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。

Prior foreign application(s)
外国での先行出願

[C1] 10-214058 (Number) (Pat. Appln.) (番号)
[C2] Japan (Country) (国名)

[C5] 10-291971 (Number) (Pat. Appln.) (番号)
[C6] Japan (Country) (国名)

[C9] (Number) (番号)
[C10] (Country) (国名)

私、第35編米国法典119条(e)項に基づいて下記の米
国特許出願規定に記載された権利をここに主張いたします。

[D1] (Application No.) (出願番号)
[D2] (Filing Date) (出願日)

私は、下記の米国法典第35編120条に基づいて下記の米
国特許出願に記載された権利、又は米国を指定している特許
協力条約365条(c)に基づき権利をここに主張します。また、
本出願の各請求範囲の内容が米国法典第35編112条
第1項又は特許協力条約で規定された方法で先行する米国特
許出願に開示されていない限り、その先行米国出願書提出日
以降で本出願書の日本国内または特許協力条約国際提出日ま
での期間中に入手された、連邦規則法典第37編1条56項
で定義された特許資格の有無に関する重要な情報について開
示義務があることを認識しています。

[E1] (Application No.) (出願番号)
[E2] (Filing Date) (出願日)

[E4] (Application No.) (出願番号)
[E5] (Filing Date) (出願日)

私は、私自身の知識に基づいて本宣言書中で私が行なう表
明が真実であり、かつ私の入手した情報と私の信じることに
基づき表明が全て真実であると信じていること、さらに故
意になされた虚偽の表明及びそれと同等の行為は米国法典第
18編第1001条に基づき、罰金または拘禁、もしくはそ
の両方により処罰されること、そしてそのような故意による
虚偽の声明を行なえば、出願した、又は既に許可された特許
の有効性が失われることを認識し、よってここに上記のごと
く宣誓を致します。

I hereby claim foreign priority under Title 35, United States
Code, § 119(a)-(d) or § 365 (b) of any foreign application(s) for
patent or inventor's certificate, or § 365(a) of any PCT
International application which designated at least one country
other than the United States, listed below and have also
identified below, by checking the box, any foreign application
for patent or inventor's certificate, or PCT International
application having a filing date before that of the application on
which priority is claimed.

Priority Not Claimed
優先権主張なし

[C3] 29/July/1998 (Day/Month/Year Filed) (出願年月日) ☐

[C7] 14/October/1998 (Day/Month/Year Filed) (出願年月日) ☐

[C11] (Day/Month/Year Filed) (出願年月日) ☐

I hereby claim the benefit under Title 35, United States Code, §
119(e) of any United States provisional application(s) listed
below.

[D3] (Application No.) (出願番号)
[D4] (Filing Date) (出願日)

I hereby claim the benefit under Title 35, United States Code, §
120 of any United States application(s), or § 365(c) of any PCT
International application designating the United States, listed
below and, insofar as the subject matter of each of the claims of
this application is not disclosed in the prior United States or PCT
International application in the manner provided by the first
paragraph of Title 35, United States Code, § 112, I acknowledge
the duty to disclose information which is material to patentability
as defined in Title 37, Code of Federal Regulations, § 1.56
which became available between the filing date of the prior
application and the national or PCT International filing date of
this application.

[E3] (Status)(patented, pending, abandoned)
(現況: 特許許可済、保属中、放棄済)

[E6] (Status)(patented, pending, abandoned)
(現況: 特許許可済、保属中、放棄済)

I hereby declare that all statements made herein of my own
knowledge are true and that all statements made on information
and belief are believed to be true; and further that these
statements were made with the knowledge that willful false
statements and the like so made are punishable by fine or
imprisonment, or both, under Section 1001 of Title 18 of the
United States Code and that such willful false statements may
jeopardize the validity of the application or any patent issued
thereon.

Japanese Language Declaration

日本語宣言書

委任状： 私は下記の発明者として、本出願に関する一切の手続きを米特許商標局に対して遂行する弁理士または代理人として、下記の者を指名いたします。（弁理士、または代理人の氏名及び登録番号を明記のこと）

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: (list name and registration number)

John H. Mion, Reg. No. 18,879; Thomas J. Macpeak, Reg. No. 19,292; Robert J. Seas, Jr., Reg. No. 21,092; Darryl Mexic, Reg. No. 23,063; Robert V. Sloan, Reg. No. 22,775; Peter D. Olexy, Reg. No. 24,513; J. Frank Osha, Reg. No. 24,625; Waddell A. Biggart, Reg. No. 24,861; Louis Gubinsky, Reg. No. 24,835; Neil B. Siegel, Reg. No. 25,200; David J. Cushing, Reg. No. 28,703; John R. Inge, Reg. No. 26,916; Joseph J. Ruch, Jr., Reg. No. 26,577; Sheldon I. Landsman, Reg. No. 25,430; Richard C. Turner, Reg. No. 29,710; Howard L. Bernstein, Reg. No. 25,665; Alan J. Kasper, Reg. No. 25,426; Kenneth J. Burchfiel, Reg. No. 31,333; Gordon Kit, Reg. No. 30,764; Susan J. Mack, Reg. No. 30,951; Frank L. Bernstein, Reg. No. 31,484; Mark Boland, Reg. No. 32,197; William H. Mandir, Reg. No. 32,156; Brian W. Hannon, Reg. No. 32,778; Abraham J. Rosner, Reg. No. 33,276; Bruce E. Kramer, Reg. No. 33,725; Paul F. Neils, Reg. No. 33,102; Brett S. Sylvester, Reg. No. 32,765; Robert M. Masters, Reg. No. 35,603; George F. Lehnigk, Reg. No. 36,359; John T. Callahan, Reg. No. 32,607 and Steven M. Gruskin, Reg. No. 36,818.

書類送付先

Send Correspondence to:
SUGHRUE, MION, ZINN, MACPEAK & SEAS, PLLC
2100 Pennsylvania Avenue, N.W. Suite 800
Washington, D.C. 20037-3213

直接電話連絡先：（名前及び電話番号）

Direct Telephone Calls to:

(202)293-7060

唯一または第一発明者名 1-00	Full name of sole or first inventor <u>Eiichi Kitazono</u>
発明者の署名 北 園 英 一 日付	Inventor's signature <u>Eiichi Kitazono</u> Date January 17, 2001
住所	Residence <u>Iwakuni-shi, Yamaguchi, Japan JPX</u>
国籍	Citizenship Japanese
私書箱	Post Office Address c/o TELJIN LIMITED <u>Iwakuni Research Center, 2-1,</u> <u>Hinodecho, Iwakuni-shi, Yamaguchi 740-0014,</u> <u>Japan</u>
第二共同発明者	Full name of second joint inventor, if any <u>Hiroyoshi Minematsu</u>
第二共同発明者 松 本 昌 日付 2-00	Second inventor's signature <u>Hiroyoshi Minematsu</u> Date January 17, 2001
住所	Residence <u>Iwakuni-shi, Yamaguchi, Japan JPX</u>
国籍	Citizenship Japanese
私書箱	Post Office Address c/o TELJIN LIMITED <u>Iwakuni Research Center, 2-1,</u> <u>Hinodecho, Iwakuni-shi, Yamaguchi 740-0014,</u> <u>Japan</u>

（第三以降の共同発明者についても同様に記載し、署名をすること）

(Supply similar information and signature for third and subsequent joint inventors.)

Japanese Language Declaration

日本語宣言書

第三の共同発明者の氏名 (該当する場合)		300	Full name of third joint inventor, if any <u>Takeyuki Kawaguchi</u>
同第三発明者の署名	日付	2001	Third inventor's signature <u>Takeyuki Kawaguchi</u> January 17, 2001
住所			Residence <u>Iwakuni-shi, Yamaguchi, Japan JPX</u>
国籍			Citizenship <u>Japanese</u>
郵便の宛先			Post office address <u>c/o TELJIN LIMITED</u> <u>Iwakuni Research Center, 2-1,</u> <u>Hinodecho, Iwakuni-shi, Yamaguchi 740-0014,</u> <u>Japan</u>
第四の共同発明者の氏名 (該当する場合)		400	Full name of fourth joint inventor, if any <u>Takanori Miyoshi</u>
同第四発明者の署名	日付	2001	Fourth inventor's signature <u>Takanori Miyoshi</u> January 17, 2001
住所			Residence <u>Iwakuni-shi, Yamaguchi, Japan JPX</u>
国籍			Citizenship <u>Japanese</u>
郵便の宛先			Post office address <u>c/o TELJIN LIMITED</u> <u>Iwakuni Research Center, 2-1,</u> <u>Hinodecho, Iwakuni-shi, Yamaguchi 740-0014,</u> <u>Japan</u>
第五の共同発明者の氏名 (該当する場合)			Full name of fifth joint inventor, if any
同第五発明者の署名	日付		Fifth inventor's signature
住所			Residence
国籍			Citizenship
郵便の宛先			Post office address
第六の共同発明者の氏名 (該当する場合)			Full name of sixth joint inventor, if any
同第六発明者の署名	日付		Sixth inventor's signature
住所			Residence
国籍			Citizenship
郵便の宛先			Post office address